



Digital Materials™ Data Sheets

Cartridges: VeroWhite, TangoBlackPlus

Primary material: VeroWhite Secondary material: TangoBlackPlus

Primary material: TangoBlackPlus Secondary material: VeroWhite

RIGID

Property	ASTM	Units	DM_8510	DM_8520	DM_8530
Tensile Strength	D-638-03	MPa	49	44	39
Modulus of Elasticity	D-638-03	MPa	2350	2150	1750
Elongation at Break	D-638-03	%	35-45	50-60	60-70
Flexural Strength	D-790-03	MPa	67	54	48
Flexural Modulus	D-790-03	MPa	2050	1700	1550
HDT at 0.45 MPa	D-648-06	°C	44	41	41
Notched Izod Impact	D-256-06	J/m	25	25	25

FLEXIBLE

Property	ASTM	Units	DM_9840	DM_9850	DM_9860	DM_9870	DM_9885	DM_9895
Tensile Strength	D-412	MPa	1	1	3	3	6	20
Elongation at Break	D-412	%	160	140	90	60	55	30
Tensile Tear Resistance	D-624 Die C	N/mm	5	6	8	13	26	46
Hardness Shore A	D-2240		40	50	60	70	85	95

Cartridges: VeroWhite, TangoPlus

Primary material: VeroWhite Secondary material: TangoPlus

Primary material: TangoPlus Secondary material: VeroWhite

RIGID

Property	ASTM	Units	DM_8410	DM_8420	DM_8430
Tensile Strength	D-638-03	MPa	49	44	39
Modulus of Elasticity	D-638-03	MPa	2350	2150	1750
Elongation at Break	D-638-03	%	35-45	50-60	60-70
Flexural Strength	D-790-03	MPa	67	54	48
Flexural Modulus	D-790-03	MPa	2050	1700	1550
HDT at 0.45 MPa	D-648-06	°C	44	41	41
Notched Izod Impact	D-256-06	J/m	25	25	25

FLEXIBLE

Property	ASTM	Units	DM_9740	DM_9750	DM_9760	DM_9770	DM_9785	DM_9795
Tensile Strength	D-412	MPa	1	1	3	3	6	20
Elongation at Break	D-412	%	160	140	90	60	55	30
Tensile Tear Resistance	D-624 Die C	N/mm	5	6	8	13	26	46
Hardness Shore A	D-2240		40	50	60	70	85	95

Cartridges: VeroWhite, TangoBlack

Primary material: VeroWhite Secondary material: TangoBlack

Primary material: TangoBlack Secondary material: VeroWhite

RIGID

Property	ASTM	Units	DM_8110	DM_8120	DM_8130
Tensile Strength	D-638-03	MPa	52	42	30
Modulus of Elasticity	D-638-03	MPa	2690	2400	1800
Elongation at Break	D-638-03	%	17	34	52
Flexural Strength	D-790-03	MPa	77	65	42
Flexural Modulus	D-790-03	MPa	2580	2190	1620
HDT at 0.45 MPa	D-648-06	°C	42	41	39
Notched Izod Impact	D-256-06	J/m	26	26	35

FLEXIBLE

Property	ASTM	Units	DM_9110	DM_9120	DM_9130
Tensile Strength	D-412	MPa	3	4	9
Elongation at Break	D-412	%	50	40	39
Tensile Tear Resistance	D-624 Die C	N/mm	8	15	47
Hardness Shore A	D-2240		80	85	95

Cartridges: FullCure720, TangoBlack

Primary material: FullCure720 Secondary material: TangoBlack

Primary material: TangoBlack Secondary material: FullCure720

RIGID

Property	ASTM	Units	DM_7210	DM_7220	DM_7230
Tensile Strength	D-638-03	MPa	56	54	47
Modulus of Elasticity	D-638-04	MPa	2300	2150	1750
Elongation at Break	D-638-05	%	15-25	15-25	15-25
Flexural Strength	D-790-03	MPa	88	84	72
Flexural Modulus	D-790-04	MPa	2500	2450	2350
HDT at 0.45 MPa	D-648-06	°C	50	49	46
Notched Izod Impact	D-256-06	J/m	24	24	24

FLEXIBLE

Property	ASTM	Units	DM_9410	DM_9420	DM_9430
Tensile Strength	D-412	MPa	3	4	9
Elongation at Break	D-412	%	50	40	39
Tensile Tear Resistance	D-624 Die C	N/mm	8	15	47
Hardness Shore A	D-2240		80	85	95

Cartridges: VeroBlue, VeroBlack**Primary material:** VeroBlue **Secondary material:** VeroBlack

RIGID

Property	ASTM	Units	DM_8210
Tensile Strength	D-638-03	MPa	48
Modulus of Elasticity	D-638-03	MPa	2750
Elongation at Break	D-638-03	%	25
Flexural Strength	D-790-03	MPa	78
Flexural Modulus	D-790-03	MPa	2570
HDT at 0.45 MPa	D-648-06	°C	41
Notched Izod Impact	D-256-06	J/m	26

Cartridges: VeroWhite, VeroBlack**Primary material:** VeroWhite **Secondary material:** VeroBlack

RIGID

Property	ASTM	Units	DM_8310	DM_8320	DM_8330
Tensile Strength	D-638-03	MPa	48	48	48
Modulus of Elasticity	D-638-03	MPa	2750	2750	2750
Elongation at Break	D-638-03	%	25	25	25
Flexural Strength	D-790-03	MPa	78	78	78
Flexural Modulus	D-790-03	MPa	2570	2570	2570
HDT at 0.45 MPa	D-648-06	°C	41	41	41
Notched Izod Impact	D-256-06	J/m	26	26	26

Cartridges: FullCure720, VeroBlack**Primary material:** FullCure720 **Secondary material:** VeroBlack

RIGID

Property	ASTM	Units	DM_Dots_7513	DM_Grid_7523
Tensile Strength	D-638-03	MPa	60.3	60.3
Modulus of Elasticity	D-638-04	MPa	2870	2870
Elongation at Break	D-638-05	%	20	20
Flexural Strength	D-790-03	MPa	75.8	75.8
Flexural Modulus	D-790-04	MPa	1718	1718
HDT at 0.45 MPa	D-648-06	°C	48.4	48.4
Notched Izod Impact	D-256-06	J/m	23.6	23.6

Cartridges: DurusWhite, Vero**Primary material:** DurusWhite **Secondary material:** VeroWhite VeroBlue VeroBlack Full-

RIGID

Property	ASTM	Units	DM_4310	DM_4410	DM_4510	DM_4710
Tensile Strength	D-638-03	MPa	33	33	33	33
Modulus of Elasticity	D-638-04	MPa	1400	1400	1400	1400
Elongation at Break	D-638-05	%	45	45	45	45
Flexural Strength	D-790-03	MPa	43	43	43	43
Flexural Modulus	D-790-04	MPa	1500	1500	1500	1500
HDT at 0.45 MPa	D-648-06	°C	43	43	43	43
Notched Izod Impact	D-256-06	J/m	42	42	42	42

Cartridges: TangoBlack, VeroBlue**Primary material:** TangoBlack **Secondary material:** VeroBlue

FLEXIBLE

Property	ASTM	Units	DM_9210	DM_9220	DM_9230
Tensile Strength	D-412	MPa	3	4	9
Elongation at Break	D-412	%	50	40	39
Tensile Tear Resistance	D-624 Die C	N/mm	8	15	47
Hardness Shore A	D-2240		80	85	95

Cartridges: TangoBlack, VeroBlack**Primary material:** TangoBlack **Secondary material:** VeroBlack

FLEXIBLE

Property	ASTM	Units	DM_9310	DM_9320	DM_9330
Tensile Strength	D-412	MPa	3	4	9
Elongation at Break	D-412	%	50	40	39
Tensile Tear Resistance	D-624 Die C	N/mm	8	15	47
Hardness Shore A	D-2240		80	85	95

Cartridges: TangoGray, TangoBlack**Primary material:** TangoGray **Secondary material:** TangoBlack

FLEXIBLE

Property	ASTM	Units	DM_9510
Tensile Strength	D-412	MPa	2
Elongation at Break	D-412	%	37
Tensile Tear Resistance	D-624 Die C	N/mm	6
Hardness Shore A	D-2240		65

Cartridges: TangoGray, VeroBlack**Primary material:** TangoGray **Secondary material:** VeroBlack

FLEXIBLE

Property	ASTM	Units	DM_9610
Tensile Strength	D-412	MPa	11
Elongation at Break	D-412	%	49
Tensile Tear Resistance	D-624 Die C	N/mm	47
Hardness Shore A	D-2240		80

All data provided herein, which is related to consumables, was collected from specific specimens and tests conditions and is provided for information only. Characteristics may vary if different specimens and test conditions are applied. Unless expressly provided in writing, no warranties are made and warranties of merchantability or fitness for a particular purpose are expressly disclaimed.

02/10

